



KR 375093B

DERWENT-ACC-NO: 2003-253987

DERWENT-WEEK: 200345

COPYRIGHT 2005 DERWENT INFORMATION LTD

TITLE: Method for manufacturing dielectric film

INVENTOR: HAN, S S

PATENT-ASSIGNEE: LG PHILIPS LCD CO LTD[GLDS]

PRIORITY-DATA: 2001KR-0024662 (May 7, 2001)

PATENT-FAMILY:

PUB-NO	PUB-DATE	LANGUAGE	PAGES	MAIN-IPC
KR 375093 B	March 8, 2003	N/A	000	H01L 021/31
KR 2002085258 A	November 16, 2002	N/A	001	H01L 021/31

APPLICATION-DATA:

PUB-NO	APPL-DESCRIPTOR	APPL-NO	APPL-DATE
KR 375093B	N/A	2001KR-0024662	May 7, 2001
KR 375093B	Previous Publ.	KR2002085258	N/A
KR2002085258A	N/A	2001KR-0024662	May 7, 2001

INT-CL (IPC): H01L021/31

ABSTRACTED-PUB-NO: KR2002085258A

BASIC-ABSTRACT:

NOVELTY - A fabrication method of a dielectric film is provided to prevent degradation of the dielectric film and to achieve thermally stable dielectric film by annealing the dielectric film using a laser.

DETAILED DESCRIPTION - A fluorinated amorphous carbon(a-C:F) is deposited on a desired layer. A laser beam is irradiated to the deposited fluorinated amorphous carbon(a-C:F), thereby forming a thermally stable dielectric film without increasing a dielectric constant of the dielectric film. At this time,

BEST AVAILABLE COPY

the irradiated laser beam is to be excited only hydrogen contained in the fluorinated amorphous carbon(a-C:F) without exciting fluorine(F). Preferably, the energy of the laser beam is 50-100 mJ/sec and the irradiated time of the laser beam is about 1-10 seconds.

CHOSEN-DRAWING: Dwg.1/10

TITLE-TERMS: METHOD MANUFACTURE DIELECTRIC FILM

DERWENT-CLASS: L03 U11

CPI-CODES: L04-C12; L04-C16A;

EPI-CODES: U11-C03D; U11-C03J2A;

SECONDARY-ACC-NO:

CPI Secondary Accession Numbers: C2003-065834

BEST AVAILABLE COPY

BEST AVAILABLE COPY

—

—

F

—

C

—

C

—

F

—

—

F

—

C

—

C

—

F

—

—

F

—

C

—

C

—

F

—

—